


MACDRAIN™ N 1080 DRAINAGE COMPOSITE

Geocomposite for planar drainage manufactured by thermobonding a draining core - HDPE geonet done by two sets of parallel overlaid ribs integrally connected to have a rhomboidal shape (GNT) - with one nonwoven geotextile (GTX), working as separation, filtration and protection layer.

	Standard	Unit	Value	Tolerance
EXTERNAL FILTER (GTX)				
Structure: needlepunched and/or thermobonded nonwoven geotextile				
Raw Material: 100% UV stabilized polyolefin				
Mass per unit area	EN ISO 9864	g/m ²	130	average value
Tensile strength MD & CMD	EN ISO 10319	kN/m	8	average value
Flux perpendicular to the plane	EN ISO 11058	l/(m ² .s)	100	average value
Characteristic opening size O ₉₀	EN ISO 12956	micron	150	average value
DRAINAGE CORE (GNT)				
Structure: sets of parallel ribs overlaid and integrally connected having a rhomboidal shape				
Raw Material: high density polyethylene, UV stabilized by carbon black, black colour				
Mass per unit area	EN ISO 9864	g/m ²	1170	typical value
Width		cm	200 or 400	typical value
GEOCOMPOSITE (GCO)				
Thickness at 2 kPa	EN 9863-1	mm	7.9	average value
Mass per unit area	EN ISO 9864	g/m ²	1300	average value
Static puncture resistance	EN ISO 12236	N	2250	average value
Tensile strength MD	EN ISO 10319	kN/m	18.0	average value
Strain at max load MD	EN ISO 10319	%	40	+/-20%
Tensile strength CMD	EN ISO 10319	kN/m	10.0	average value
In plane flow capacity MD	EN ISO 12958	l/(m.s)	l/(m.s)	average value
	gradient i =	1.0	1.0	
	type of contact	S/S	R/R	
	20 kPa	-	2.20	
	100 kPa	-	1.90	
	500 kPa	-	1.50	
STANDARD DIMENSIONS OF GEOCOMPOSITE				
Roll height		m	2.0 or 4.0	typical value
Length		m	25 - 50	typical value
Filter overlay (one side)		mm	100	typical value



MD = longitudinal direction
 CMD = trasversal direction
 S/S = contact type soft/soft
 R/R = contact type rigid/rigid

The producer, for his optimisation and improving process of the product's technical characteristics, has the faculty to modify the standards and the characteristics of the product without any pre-advise. All the information are given in base to our experience; in any case no responsibility for an incorrect use could be referred to the producer or one of his distributors.

Officine Maccaferri S.p.A.

Via Kennedy, 10 - 40069 Zola Predosa (BO) - Italy

Tel. (+39) 051-6436000 - Fax (+39) 051-6436201

E-mail: comes@maccaferri.com - Web site: www.officinemaccaferri.com

Bureau Veritas Certified Quality System Company
 with SINCERT's and UKAS's accreditation.