

MACGRID AR range 10.7®

GEOGRIDS & GEOCOMPOSITES FOR ASPHALT REINFORCEMENT APPLICATIONS

MACGRID® AR .7 and the composite of the AR G.7 type (geogrid in combination with a nonwoven geotextile) are planar structures consisting in glass fiber strands arranged in a grid shape with squared polymeric coated mesh and - on request - with a pressure sensitive adhesive (AR A.7). The full range of MACGRID® AR material has been specially developed for asphalt reinforcement (i.e. highway, airport) and industrial pavement applications.

MACGRID AR		10.7	10A.7	10G.7
Mechanical Properties				
Minimum tensile strength - Longitudinal direction ⁽¹⁾	kN/m	100	100	100
Typical strain at max. load - Longitudinal direction	%	2.5 ±1	2.5 ±1	2.5 ±1
Minimum tensile strength - Cross direction	kN/m	100	100	100
Typical strain at max. load - Cross direction ⁽¹⁾	%	2.5 ±1	2.5 ±1	2.5 ±1
Young Modulus	GPa	76	76	76
Physical-Chemical Properties				
Geogrid structure		Glass fiber strands		
Coating		Bitumen compatible polymer		
Pressure sensitive adhesive		no	yes	no
Separation nonwoven geotextile impregnated with bitumen compatible polymer coating		no	no	yes
Working temperature	°C	from ½100 to +280		
Melting point	°C	1000		
Mass per unit -nominal value	g/m ²	530	545	560
Mesh opening size -nominal value ⁽²⁾	mm	25 x 25		
Roll width -nominal value ⁽³⁾	m	from 2.2 to 5.3		
Roll length -nominal value	m	100		

(1) The tensile strength value is based on the component strand resistance and/or on ASTM D6637-91 method A or EN ISO 10319


(2) The mesh opening size has a 10% tolerance. Other mesh sizes i.e. 12.5x12.5 and 40x40 or other ones are available on request ; to be verified feasibility with the technical-commercial dpt.

(3) The standard width of the roll is 4, 4.4/2.2 and 5.3/2.65 mts. Other sizes available according to stock availability.

- The standard geotextile used in the gecomposite range G.7 has a typical mass per unit of 13 gr/m²; other types of non-woven geotextiles can be used on request;
- The adhesive used in the A.7 type geogrids is 'self-adhesive'; this special glue is activated by a simply pressure during the installation operations;
- The gecomposite and geogrid range is available in other strengths. For more and detailed information on the full range please contact our technical-commercial dpt.

MacGrid AR .7 or A.7

MacGrid AR .7 type G



For the optimisation and improvement process of the technical characteristics of the products, the manufacturer reserves the right to modify the standard characteristics of the product without any notice. The information contained herein are to the best of our knowledge accurate, but since the circumstances and conditions in which it may be used are beyond our control, we do not accept any liability for any loss or damage, however arising, which results directly or indirectly from the use of such information nor we do offer any warranty or immunity against patent infringement.

Officine Maccaferri S.p.A.

Via Kennedy, 10 - 40069 Zola Predosa (BO) - Italy
Tel. (+39) 051-6436000 - Fax (+39) 051-6436201

E-mail: comes@maccaferri.com - Web site: www.officinemaccaferri.com

Bureau Veritas Certified Quality System Company
with SINCERT's and UKAS' s accreditation.